

SHAVING NET (INDEX 3.2 x 3.2 MM - 90 GR - R72)



INDEX

1. Data and Documentation
2. Use
3. Specifications

1. DATA AND DOCUMENTATION

| Code | Description | Dimensions (mm) | Weight | Colour | Pkg. / Pallet |
|------------|-------------|-----------------|---------|--------|--|
| RET01-1010 | Shaving Net | 1.00 x 50 m | 90 g/m2 | White | 50 m ² / 2,250 m ² |

MATERIAL

Made of Adfors Saint-Gobain type E glass fibre, impregnated with SBR anti-alkaline resins, spacing 3.2 x 3.2 mm and weight of 90 g/m2.

| Features | Units of Measurement | RET01-1010 | |
|--------------------------|----------------------|-------------------------------------|------|
| | | Warp | Plot |
| Setting | for 10 cm | 28 x 2 | 25 |
| Weight per thread (Tex) | gr/1000 m | 68 | 136 |
| Standard Height | cm | | 100 |
| Roll length | m | | 50 |
| Thickness Treated Fabric | mm | | 0,32 |
| Raw Fabric Weight | g/m2 | | 72 |
| Thickness Treated Fabric | min g/m2 | | 90 |
| Fuel Content (LOI) | % of mass | | 18 |
| Treatment Type | | Alkali-resistant without emollients | |
| Dimensions Wheelbase | mm | 3,2 x 3,2 | |

Tensile strength (TS) and elongation:

Minimum tensile strength (N/50 mm) and maximum elongation (%) is ascertained according to DIN EN ISO 13934-1 as follows

| Deposition method | Traction resistance | | Elongation |
|---------------------|---------------------|------------------|---------------|
| | Nominal Value | Individual Value | Average Value |
| Standard Conditions | 800 / 750 | 800 / 700 | 3,5 / 3,5 |
| Solution 5% NaOH | 250 / 350 | 235 / 250 | 3,5 / 3,5 |
| Quick Test | 1200 / 1200 | 400 / 350 | 4,0 / 4,0 |

Tolerances:

Setting: ± 5% in Warp and Weft
 Height: ± 1%
 Length: ± 2%
 LOI: ± 3%

Quality Inspection

The mode of quality control, taking samples and shooting the material, is according to standard 0326 works. Packing:

The rolls are packed vertically in cardboard boxes on a pallet. Warehouse:

Rolls must be stored in a dry place. Storage temperature -10 °C to + 50 °C.

2. USE

Used in levelling to avoid cracks in gypsum-based finishes and at joints between materials with different expansion coefficients by evenly distributing the stresses to which they are subjected. Mesh with a higher breaking load than R58 mesh (Art. RET01-1000); also acceptable solution for external levelling. With high wettability and adaptability to all products on the market. The function of this mesh is to prevent cracking in the presence of gypsum-based finishes and at joints between materials with different expansion coefficients by evenly distributing the stresses to which they are subjected.

SHAVING NET (INDEX 3.2 x 3.2 MM - 90 GR - R72)

3. SPECIFICATION ITEMS

| Entry | Description | U.M. | Price |
|-------------------------|---|----------------|-------|
| Dak.B.RET01.1010 | <p>Supply and laying of white mesh (identification code R72, corresponding to the weight per square metre of pure glass fibre net of resin), h.1.00 x 50 m. Packaged in shrink-wrapped rolls. Made of Adfors Saint-Gobain type E glass fibre, impregnated with SBR anti-alkaline resins, spacing 3.2 x 3.2 mm and weight of 90 g/m². Used in skimming to prevent cracks in gypsum-based finishes and at joints between materials with different expansion coefficients by evenly distributing the stresses to which they are subjected. Mesh with a higher breaking load than R58 mesh (Art. RET01-1000); also acceptable solution for external skimming. With high wettability and adaptability to all products on the market. The function of this mesh is to prevent cracking in the presence of gypsum-based finishes and at joints between materials with different expansion coefficients by evenly distributing the stresses to which they are subjected. Dimensions 1.00 x 50 m.....</p> | m ² | - |